



A wide variety of bullnose, cove and corner trims and mosaics tiles are available for you to complete projects for total design aesthetics. Refer to **StonePeak Ceramics Product Catalogue**

**1. PRODUCT NAME**

**Cappuccino Collection  
Data Sheet 260.00**

**2. MANUFACTURER**

**StonePeak Ceramics, Inc.**  
 314 West Superior  
 Chicago, IL 60610  
 Telephone: 312.506.2800  
 Fax: 312.335.0533  
 Email: [info@stonepeakceramics.com](mailto:info@stonepeakceramics.com)  
 Website: [www.stonepeakceramics.com](http://www.stonepeakceramics.com)

**3. PRODUCT DESCRIPTION**

**Cappuccino** – Variation in the shades, movement in the pattern and warm colors make this collection an all-time favorite. This line has an added anti-slip ingredient which make it suitable also for high traffic applications.

**Recommended Applications:**

Ideally suited for commercial and residential settings such as hotel lobbies, restaurants, shopping malls, schools, and residential floors and walls.

**Finishes/Textures:**

Glazed Finish; Calibrated

**Size/thickness:**

12" x 12" x 3/8" nominal (8.5 mm)  
 18" x 18" x 3/8" nominal \*(9.0 mm)  
 \*denotes work size per ISO 10545-2

**Recommended Grout Joint: 1/8" or greater**

Grout joints of 1/8" inch or less, especially with larger format tiles or running bond patterns, may require floor flatness values in excess of the 1/4" in 10' (or 1/16" in 1.0') standard required by ANSI.

For patterns with running bond/brick joint patterns StonePeak recommends a maximum of 33% offset.  
**StonePeak Ceramics Trim System:**

**4. TECHNICAL DATA**

Physical Properties	ASTM Test	Industry Standards	StonePeak Results
Water Absorption	C373	Impervious < 0.5%	≤ 0.1 %
COF Average	C1028	No Requirement	≥ 0.80 Dry ≥ 0.70 Wet
Freeze Thaw Cycling	C1026	No Requirement	No Evidence Of Damage
Hardness (Mohs)		No Requirement	7
Warpage Average	C485	Warpage +/- 0.75% on any edge	≤0.75%
Warpage Average	C485	Warpage +/- 0.50% on diagonal	≤0.50%
Wedging Average	C502	Wedging +/- 0.50%	≤0.50%
Breaking Strength	C648	250 lbf or greater	> 400 lbf
Glazed Wear	C1027	No Requirement	NA
Aesthetic Class/Shade Rating		No Requirement	V3

COF: all values given are for matte or honed material. No values are given for polished material. StonePeak does not recommend polished surfaces in areas subject to exposure from grease, oil or water.

**5. INSTALLATION**

**Surface Preparation:**

All installation work using StonePeak Ceramics tiles will conform to the standards set forth in the latest version of ANSI A108/118 and/or the TCA Handbook for Ceramic Tile installations.

All substrates should be between 40 degrees F and 90 degrees F and structurally sound, clean and free of all dirt, oil, grease, paint, concrete sealers or curing compounds as per ANSI A108.01.

**Deflection:**

Substrate must conform to all state and local building code requirements and ANSI A108.01 for maximum allowable substrate deflection.

Movement Joints:

Movement joints shall be provided throughout the tile and work will conform to ANSI Specification A108.01-3.7; A108.02 – 4.4.and TCA Details EJ171.

Installation or setting materials:

Setting materials used will conform to the ANSI 118.4 standard or greater and be recommended by the selected manufacturer for the installation & setting materials for ceramic or porcelain tile based on the application requirements.

## 6. AVAILABILITY AND COST

**StonePeak Cappuccino Collection** is available from select distributors of ceramic tile and stone.

To find accessible information of delivery and product costs for your area, please contact your nearest StonePeak Ceramics representative.

**See section 2 for available phone numbers and contact information.**

## 7. WARRANTY

**StonePeak Ceramics** guarantees that its products will be free of manufacturing defects and they will meet or exceed the performance specifications set forth in ANSI 137.1.

For further information and details please contact your nearest StonePeak Ceramics Distributor or StonePeak Ceramics representative for a written copy of the warranty information.

**See section 2 for available phone numbers and contact information.**

## 8. MAINTENANCE

**Care and Maintenance Recommendations Guide**

Please refer to **StonePeak Ceramics Care and Maintenance Recommendations Guide** for all technical information as to the care of this collection.

## 9. TECHNICAL SERVICES

### Technical Assistance

Guide Specifications, literature, MSDS, tile samples, details and installation procedures are all available for your use or libraries.

Please contact your nearest StonePeak representative for catalogues, physical samples, architectural binders or StonePeak Architectural Resource CD-ROM.

**Continued Education Programs** are available – **1 or 2 hour HSW Learning Units** – contact StonePeak Ceramics' main office to set up a presentation.

## 10. FILING SYSTEMS

### DS 260.00 – Cappuccino Collection



**Caramel Cappuccino**



**Chocolate Cappuccino**

**Note to Specifier: Click on color with Internet Connection to hyperlink directly to product color data at the StonePeak Ceramics website.**