

Stonepeak Ceramics, Inc.
Corporate Headquarters
720 N Franklin St., Ste 500
Chicago, IL 60654 US

Production Plant
238 Porcelain Tile Dr.
Crossville, TN 38555 US

TECHNICAL DATA SHEET

TOUCH COLLECTION

Size/Thickness:







12" x 24" x 5/16" (8 mm) nominal

Colors:

Evening Sunset, Pearl Essence, Summer Breeze, Sun Glow

Finishes:

Honed*

| | | | | | |
|---|--|--|--|--|--|
|  4 VISIBLE ABRASION RESISTANCE |  7 MOHS |  <p>Dry .83 Wet .63 Dynamic .58 (BOT 3000)</p> <p>C.O.F.</p> |  0.05% WATER ABS |  CLASS A CHEMICAL RESISTANCE |  502 lbf BREAKING STRENGTH |
|---|--|--|--|--|--|

* All values given are for matte or honed material. No values are given for polished material. Stonepeak does not recommend polished surfaces in area subject to exposure from grease, oil or water.

For level interior spaces to be walked upon when wet (see ANSI A137.1 section 6.2.2.1.10 – Section 9.6 for test procedure).

Guide specifications, literature, SDS, tile samples, details and installation procedures are all available for your use at our libraries. Please contact your nearest Stonepeak representative for merchandising.

Rev. July 30, 2024