

DOLCISSIMA 12MM

Porcelain tile classified as Impervious Group P1 is frost-resistant and chemically resistant. These characteristics are achieved through the dry-forming of high-quality mixtures composed of atomized and blended natural raw materials, such as kaolin minerals and feldspars.


Collection Description

Company	Stonepeak Ceramics
Collection	Dolcissima 12mm
Finishes	Natural Silky Polished
Glazed/Unglazed	Glazed
Thickness in inch	1/32in
Thickness in mm	12mm
Rectified	No

Available Colors



Arabescato Grey



Beleza



Brilho Azul




Calacatta Antique



Oro Calacatta



Calacatta White



Cementi Grey



Creamy Basalt




Crystal Onyx



Grey Basalt



Grigio Trambisera



Invisible Grey



Lasa Argento




Luxe White



Macchia Vecchia




Marine Opulence




Mystic Cascade




Namibia White




Nero Marquinia




Pietra Bianca




Pietra Grey



Pietra Scura



Pure White



Sand Basalt



Savoie Blue




Silver Serenity



Statuarietto

Nominal Sizes

Slab Tile



126"x60"

Bookmatch*



Bookmatch Available

(*) Please note that book-match items are not rectified. As a result, the two faces will not perfectly align unless a rectifying process is completed beforehand.

DOLCISSIMA 12MM

Product Dimensions (Unrectified)

Nominal Size (in)	Actual (in)	Nominal Size (cm)	Actual (mm)
60 x 126 in		150 x 320 cm	

Please note that book-match items are not rectified. As a result, the two faces will not perfectly align unless a rectifying process is completed beforehand.

For more information about this collection scan below



Technical Features

Physical Properties	Norms	Required Standards	Stonepeak Results ⁽¹⁾
Water Absorption	ASTM C 373 - 18	Impervious $\leq 0.5\%$	$\leq 0.5\%$
Thickness Variation	ASTM C 499 - 20	± 0.02 inch	± 0.02 inch
Facial Dimension	ASTM C 499 - 20	± 0.25 %	± 0.25 %
Warpage Average Diagonal	ASTM C 485 - 16	± 0.40 %	± 0.40 %
Warpage Average Edge	ASTM C 485 - 16	± 0.40 %	± 0.40 %
Wedging	ASTM C 502 - 16	± 0.25 %	± 0.25 %
Bond Strength	ASTM C 482 - 20	≥ 50 psi	≥ 50 psi
Breaking Strength	ASTM C 648 - 20	≥ 275 lbf	≥ 275 lbf
Hardness (Mohs)	ASTM C 1895 - 20	Range 0 - 10	≥ 7 ⁽²⁾
Frost Resistance	ASTM C 1026 - 13 (2018)	No sample must show alterations to surface	No evidence of damage
Chemical Resistance	ASTM C 650 - 20	Range A / E	Class A ⁽³⁾
Stain Resistance	ASTM C 1378 - 20	Range A / E	Class A ⁽³⁾
Fire Resistance	ASTM E84	Class A	Class A1-A1FL

Result Notes


- (1) All values given are for textured/natural/structured finish. Values for different finishes are available upon request.
- (2) Mohs result referring to textured/natural finish. For polished/semi-polished/silky finish: ≥ 6 .
- (3) Chemical and stain resistance refer to textured/natural finish. For polished/silky finish tests are provided on request. For more detailed information, refer to ANSI A137.1 Specifications for Ceramic Tile.

DOLCISSIMA 12MM


Technical Features: Visual Evaluation Shade & Texture

Visual Evaluation


V1




V2



V3



V4




TCNA rates tile color and texture variation on a scale up to V4, with V4 indicating the highest variation.

This porcelain tile is rated V2, meaning moderate variation in tone, primarily consistent with slight differences between tiles.

Recommended Grout Joint

Recommended grout joint is 3/16" or greater.

Grout joints of 1/8" inch or less, especially with larger format tiles or running bond patterns, may require floor flatness values in excess of the 1/4" in 10' (or 1/16" in 1.0') standard required by ANSI.



For patterns with running bond/brick joints, Stonepeak recommends a maximum of 33% offset.

Technical Features: Recommended Use

Visible Abrasion Resistance ratings are based on ASTM C1027-19 testing, which measures surface wear under abrasive load, combined with our manufacturer-declared results.

Class 1	Class 2	Class 3	Class 4
Residential Bathrooms	All Residential Areas	All Residential / Light Commercial	All Residential / Commercial
Nero Marquina	Pietra Grey, Pietra Scura, Brilho Azul	Grey Basalt, Cement Grey, Savoie Blue, Sand Basalt, Creamy Basalt	Pure White, Arabescato Grey, Calacatta Antique, Calacatta Oro, Calacatta SW, Luxe White, Pietra Bianca, Statuarietto, Grigio Trambisera, Invisible Grey, Lasa Argento, Macchia Vecchia, Beleza, Christal Onyx, Marine Opulence, Mystic Cascade, Namibia White, Silver Serenity

Pre-Consumer Recycled Content

This porcelain product, manufactured at the Crossville, TN factory, contains at least **40% pre-consumer recycled content**, with all claims certified by Bureau Veritas Certification. Recycled content is a LEED metric intended to increase demand for building materials that incorporate reused or repurposed materials.



ISO 14021:2022 CONTENT OF RECYCLED MATERIAL
Rev.15 - Issued 7.31.2024 Expired 9.03.2027

DOLCISSIMA 12MM

Technical Features: DCOF - Wet Test

Norm	Standard	Stonepeak Result ⁽⁴⁾
ANSI A 326.3 - 2021	≥0.42	≥0.42 + Natural, Silky, Polished

Product Use Recommendation

Finish	Classification	Criteria
Natural, Silky, Polished	Interior Dry (ID)	≥ 0.42 dry DCOF
Natural	Interior Wet (IW)	≥ 0.42 wet DCOF

More information can be found at: (<https://tcnatile.com/resource-center/dynamic-coefficient-of-friction/>)

Result Notes

- (4) DCOF results referring to textured/natural/structured products are performed with the WET test, while for polished, semi-polished and silky the DCOF test is performed DRY.
- (4) The DCOF values shown in the catalog, website, or other sales documents are for reference only and are non-binding. Any specific requirements must be confirmed by us at the time of order and, in any case, always prior to installation.
- (4) All values given are for textured/natural/structured finish.

Certifications, Memberships and Validations

Product Certifications and Validations



Organizational Memberships & Other Validations



More information

For more information regarding Product Care and Maintenance, Warranty and other technical documents refer to our Stonepeak Document Library: (www.stonepeakceramics.com/document-library/).

For more information scan below



Stonepeak Ceramics, Inc.
Corporate Headquarters
720 N Franklin St., Ste 500
Chicago, IL 60654 US

Production Plant
238 Porcelain Tile Dr.
Crossville, TN 38555 US

The technical data reported in this Technical Data Sheet are indicative and non-binding. The company reserves the right to make changes at any time without prior notice. Always refer to the latest available version of this document.