

PORCELAIN TILE

UNGLAZED / GLAZED

Glazed

THICKNESS

8mm | 20mm

FINISHES

Structured | Flamed | Natural Plus | Antislip

SIZES

48"x48" | 40"x40" | 24"x48" | 24"x24" | 12"x12"

COLORS

Baycliff Black | Forest Green | Moon Cream |
Limestone Beige | Silver Grey

Scan for more
product details.



Nominal Size (in)	Actual (in)	Nominal Size (mm)	Actual (mm)	Rectified
48" x 48"	47.40" x 47.40"	1200 x 1200mm	1995.8 x 1995.8mm	Yes
40" x 40"	39.37" x 39.37"	1000 x 1000mm	1000 x 1000mm	Yes
24" x 48"	23.70" x 47.40"	600 x 1200mm	602 x 1204mm	Yes
24" x 24"	23.70" x 23.70"	600 x 600mm	602 x 602mm	Yes
12" x 24"	11.73" x 23.70"	300 x 600mm	298 x 602mm	Yes

PERFORMANCE

		PROPERTY	NORMS	STANDARD	STONEPEAK RESULT ⁽¹⁾
SLIP RESISTANCE		SLIP RESISTANCE: DCOF (DRY)	ANSI A 326.3 - 2021	≥0.42 Dry	≥0.42 Interior Dry (ID) Structured ⁽⁴⁾ ≥0.55 Interior Dry (ID) Natural Plus, Flamed ⁽⁴⁾ ≥0.70 Interior Dry (ID) Antislip ⁽⁴⁾
		SLIP RESISTANCE: DCOF (WET)	ANSI A 326.3 - 2021	≥0.42 Wet	≥0.42 Interior Wet (IW) Structured ⁽⁴⁾ ≥0.55 Interior Wet (IW) Natural Plus, Flamed ⁽⁴⁾ ≥0.70 Interior Wet (IW) Antislip ⁽⁴⁾
PHYSICAL PROPERTIES		WATER ABSORPTION	ASTM C 373 - 18	Impervious ≤0.5%	≤0.5%
		BOND STRENGTH	ASTM C 482 - 20	≥ 150 psi	≥ 150 psi
		BREAKING STRENGTH	ASTM C 648 - 20	≥ 175 lbf	≥ 175 lbf
		HARDNESS (MOHS)	ASTM C 1895 - 20	Range 0 - 10	≥ 7 ⁽²⁾
		VISUAL EVALUATION	VISUAL VALUATION SHADE & TEXTURE	Range V1 - V4	V3
		ABRASION RESISTANCE	ASTM C1027-19	Class 1 - Class 4	Available Upon Request
CHEMICAL PROPERTIES		CHEMICAL RESISTANCE	ASTM C 650 - 20	Range A / E	Class A ⁽³⁾
		STAIN RESISTANCE	ASTM C 1378 - 20	Range A / E	Class A ⁽³⁾
		FROST RESISTANCE	ASTM C 1026 - 13 (2018)	No sample must show alterations to surface	No evidence of damage
		FIRE RESISTANCE	ASTM E84	Class A	Class A1-A1FL
TECHNICAL FEATURES		THICKNESS VARIATION	ASTM C 499 - 20	± 0.04 inch	± 0.04 inch
		FACIAL DIMENSION	ASTM C 499 - 20	± 0.25 %	± 0.25 %
		WEDGING	ASTM C 502 - 16	± 0.25 %	± 0.25 %
		WARPAGE AVERAGE DIAGONAL	ASTM C 485 - 16	± 0.40 %	± 0.40 %
		WARPAGE AVERAGE EDGE	ASTM C 485 - 16	± 0.40 %	± 0.40 %

The material meets compliance with the requirements of America standards ANSI A 137.1: June 2021, ANSI A326.3 - 2021 and ASTM Section 15 Volume 15.02.

- (1) All values given are for textured/natural/structured finish. Values for different finishes are available upon request.
 (2) Mohs result referring to textured/natural finish. For polished/semi-polished/silky finish: ≥ 6.
 (3) Chemical and stain resistance refer to textured/natural finish. For polished/semi-polished/silky finish tests are provided on request. For more detailed information, refer to ANSI A137.1 Specifications for Ceramic Tile.
 (4) DCOF results referring to textured/natural/structured products are performed with the WET test, while for polished, semi-polished and silky the DCOF test is performed DRY.
 (4) The DCOF values shown in the catalog, website, or other sales documents are for reference only and are non-binding. Any specific requirements must be confirmed by us at the time of order and, in any case, always prior to installation.
 (4) All values given are for textured/natural/structured finish. Values for different finishes are available upon request.

Product Certifications and Validations



Organizational Memberships

