

UNGLAZED / GLAZED

Glazed

THICKNESS

7.5mm

FINISHES

Glossy

SIZES

6"x6" | 3"x6"

COLORS

Geo Azzurro | Geo Bianco | Geo Blu | Geo Oro |
Geo Rosso | Geo Verde | Decoro Geo Azzurro |
Decoro Geo Bianco | Decoro Geo Blu |
Decoro Geo Rosso | Decoro Geo Verde |
Decoro Oro Geo Azzurro | Decoro Oro Geo Blu |
Decoro Oro Geo Bianco | Decoro Oro Geo Rosso |
Decoro Oro Geo Verde



Nominal Size (in)	Actual (in)	Nominal Size (mm)	Actual (mm)	Rectified
6" x 6"		100 x 300mm		No
3" x 6"		100 x 300mm		No

PERFORMANCE

PERFORMANCE		PROPERTY	NORMS	STANDARD	STONEPEAK RESULT ⁽¹⁾
PHYSICAL PROPERTIES		WATER ABSORPTION	ASTM C 373 - 18	P4	7.0% < P4 ≤ 20.0 %
		BREAKING STRENGTH	ASTM C 648 - 20	≥ 125 lbf	≥ 125 lbf
		VISUAL EVALUATION	VISUAL VALUATION SHADE & TEXTURE	Range V1 - V4	V2
		CRAZING RESISTANCE	ASTM C424 - 20	Pass	Pass

CHEMICAL PROPERTIES		THERMAL SHOCK	ASTM C 484 - 20	Pass	Pass ⁽²⁾
---------------------	---	---------------	-----------------	------	---------------------

TECHNICAL FEATURES		THICKNESS VARIATION	ASTM C 499 - 20	0.031 inch (0.79mm)	0.031 inch (0.79mm)
		FACIAL DIMENSION	ASTM C 1378 - 20	± 0.018 in size < 6"	± 0.018 in
				± 0.30% size ≥ 6"	± 0.30%
		WARPAGE AVERAGE DIAGONAL	ASTM C 485 - 16	- 0.018 in / + 0.024 in size < 6"	- 0.018/+ 0.024 in
		WARPAGE AVERAGE EDGE		- 0.30% / + 0.40 % size ≥ 6"	- 0.30% / + 0.40 %
					- 0.018 in / + 0.024 in size < 6"
		WEDGING	ASTM C 502 - 16	- 0.30% / + 0.40 % size ≥ 6"	- 0.30% / + 0.40 %
				± 0.024 in size < 6"	± 0.024 in
		± 0.40 % size ≥ 6"	± 0.40 %		

(†) All values given are for textured/natural/structured finish. Values for different finishes are available upon request.

Product Certifications and Validations



Organizational Memberships

