

CERAMIC WALL TILE

UNGLAZED / GLAZED

Glazed

THICKNESS

7.5mm

FINISHES

Glossy

SIZES

4"x12"

COLORS

Caramel | Emerald | Grey | Mink | Ocean |
Sand | WhiteScan for more
product details.

Nominal Size (in)	Actual (in)	Nominal Size (mm)	Actual (mm)	Rectified
4" x 12"		100 x 300mm		No

PERFORMANCE

		PROPERTY	NORMS	STANDARD	STONEPEAK ⁽¹⁾ RESULT
PHYSICAL PROPERTIES	 	WATER ABSORPTION	ASTM C 373 - 18	P4	7.0% < P4 ≤ 20.0 %
		BREAKING STRENGTH	ASTM C 648 - 20	≥ 125 lbf	≥ 125 lbf
		VISUAL EVALUATION	VISUAL VALUATION SHADE & TEXTURE	Range V1 - V4	V2
		CRAZING RESISTANCE	ASTM C424 - 20	Pass	Pass

CHEMICAL PROPERTIES		THERMAL SHOCK	ASTM C 484 - 20	Pass	Pass ⁽²⁾
------------------------	--	---------------	-----------------	------	---------------------

TECHNICAL FEATURES	  	THICKNESS VARIATION	ASTM C 499 - 20	0.031 inch (0.79mm)	0.031 inch (0.79mm)
		FACIAL DIMENSION	ASTM C 1378 - 20	± 0.018 in size < 6"	± 0.018 in
				± 0.30% size ≥ 6"	± 0.30%
		WARPAGE AVERAGE DIAGONAL	ASTM C 485 - 16	- 0.018 in / + 0.024 in size < 6"	- 0.018/+ 0.024 in
		WARPAGE AVERAGE EDGE		- 0.30% / + 0.40 % size ≥ 6"	- 0.30% / + 0.40 %
				- 0.018 in / + 0.024 in size < 6"	- 0.018/+ 0.024 in
		WEDGING	ASTM C 502 - 16	± 0.024 in size < 6"	± 0.024 in
				± 0.40 % size ≥ 6"	± 0.40 %

The material meets compliance with the requirements of America standards
ANSI A 137.1: June 2021, ANSI A326.3- 2021 and ASTM Section 15 Volume 15.02.

⁽¹⁾ All values given are for textured/natural/structured finish. Values for different finishes are available upon request.

⁽²⁾ Chemical and stain resistance refer to textured/natural finish. For polished/silky finish tests are provided on request. For more detailed information, refer to ANSI A137.1 Specifications for Ceramic Tile.

Product Certifications and Validations



Organizational Memberships

